



FEEL THE SW
DIFFERENCE®

DESIGNED TO ENHANCE WORKER PERFORMANCE.



PowerForm®

PF-95BK

POWDER-FREE ECOTEK SUSTAINABLE
NITRILE EXAMINATION GLOVES*

**PROTECT HANDS AND THE ENVIRONMENT
WITH A SUSTAINABLE GLOVE THAT COMBINES
DURABILITY AND TACTILE SENSITIVITY FOR
CRITICAL TASKS***

- EcoTek® Sustainable Technology*
- Silicone-free for critical environments
- Exceeds 1.5 AQL laboratory standards

PF

PF-95BK

WEIGHT	LENGTH	THICKNESS	FEATURES	COLOR
 6.5g (large size)	 9.5"	 5.0 mil	EcoTek® Clean Washed Air Inspected	 BLACK

ecotek



Optimal thickness
for durability and
tactile sensitivity

Fully textured
surface for wet
and dry grip

Tear-resistant
beaded cuff for
easy donning



Find it at fishersci.com and fishersci.ca

fisher scientific
part of Thermo Fisher Scientific

TECHNICAL DATA



PF-95BK

POWDER-FREE ECOTEK SUSTAINABLE
NITRILE EXAMINATION GLOVES*

PRODUCT DESCRIPTION

SPECIFICATIONS	
PRODUCT	PowerForm®
GRADE	Powder-Free Exam
MATERIAL	Nitrile
THICKNESS FINGER	5.6mil 0.14mm
PALM	5.0mil 0.13mm
CUFF	4.1mil 0.10mm
COLOR	Black
SURFACE	Fully Textured
LENGTH	9.5" 242mm
WEIGHT	6.5g
FIT TYPE	Ambidextrous
CUFF TYPE	Beaded
WATERTIGHT AQL	1.5
ORIGIN COUNTRY	China

PHYSICAL PROPERTIES

	PRE-AGING	POST-AGING
TENSILE		
STRENGTH:	22 MPA	20 MPA
ELONGATION:	540%	520%

INTEGRATED TECHNOLOGIES

ECOTEK Sustainable Technology: Product has been tested per ASTM D5526*

100% Air Inspected

Clean Washed



* Specifications based on size Large glove

STANDARDS & CERTIFICATIONS

EN ISO 21420:2020
EN 455-2000-2015
ASTM D6319-19
ASTM F1671-13
ASTM F739-12
Reach EU 1907/2006
EU 2016/425

CAT III Complex Design
FDA 21 CFR 177.2600



CE 0493



Please visit [swssglobal.com/symbols](https://www.swssglobal.com/symbols) for information on standards used on this document.

ORDERING

CAT NO.	MFG NO.	SIZE	PALM WIDTH	PACKAGING
17441080	N716882	S 6½ – 7	3.5" 89mm	100 gloves per box 10 boxes per case
17441081	N716883	M 7½ – 8	3.8" 98mm	100 gloves per box 10 boxes per case
17441015	N716884	L 8½ – 9	4.3" 108mm	100 gloves per box 10 boxes per case
17441016	N716885	XL 9½ – 10	4.6" 116mm	100 gloves per box 10 boxes per case
17441084	N716886	2XL 10½ – 11	5.0" 126mm	100 gloves per box 10 boxes per case

* EcoTek gloves tested to ASTM D5526-12 Standard Test Method for Determining Anaerobic Biodegradation of Plastic Materials Under Accelerated Landfill Conditions. Results are 92.6% biodegradation in 60% solids landfill at 945 days. Future results cannot be predicted/extrapolated. If you need more information on the test reports, send email to cs@swssglobal.com.

APPLICATIONS

Chemical Handling
Tattooing and Cosmetics

Keep out of sunlight. Store in a cool, dry place.
Keep away from sources of ozone or ignition.



R_N71688X0923

Distributed by Fisher Scientific. Contact us today:

In the United States
Order online: fishersci.com
Call customer service: 1-800-766-7000

In Canada
Order online: fishersci.ca
Call customer service: 1-800-234-7437



© 2024 Thermo Fisher Scientific Inc. All rights reserved. BN247866671-NA
Trademarks used are owned as indicated at fishersci.com/trademarks.