



FEEL THE SW
DIFFERENCE®

DESIGNED TO ENHANCE WORKER PERFORMANCE.



PF-95BL

POWDER-FREE ECOTEK SUSTAINABLE
NITRILE EXAMINATION GLOVES WITH DRY CORE*

**KEEP HANDS COOLER AND MORE COMFORTABLE
WITH PREMIUM EXAM QUALITY NITRILE GLOVES,
FEATURING UNIQUE DRY CORE MOISTURE
MANAGEMENT TECHNOLOGY.**

- Dry Core® Moisture Management Technology pulls sweat away from the skin
- EcoTek® Sustainable Technology*
- Silicone-free for critical environments

PF

PF-95BL

WEIGHT	LENGTH	THICKNESS	FEATURES	COLOR
 8.5g (large size)	 9.5"	 6.1 mil	Dry Core® EcoTek®	 BLUE


ECOTEK



ANSI Level 3
Abrasion
Protection

Fully textured
surface for wet
and dry grip

Tear-resistant
beaded cuff for
easy donning



TECHNICAL DATA



PF-95BL

POWDER-FREE ECOTEK SUSTAINABLE
NITRILE EXAMINATION GLOVES WITH DRY CORE*

PRODUCT DESCRIPTION

SPECIFICATIONS

PRODUCT		PowerForm®	
GRADE		Powder-Free Exam	
MATERIAL		Nitrile	
THICKNESS	FINGER	6.9mil	0.18mm
	PALM	6.1mil	0.16mm
	CUFF	5.1mil	0.13mm
COLOR	OUTER	Blue	
	INNER	White	
SURFACE	OUTER	Fully Textured	
	INNER	Dry Core®	
LENGTH		9.5"	242mm
WEIGHT		8.5g	
FIT TYPE		Ambidextrous	
CUFF TYPE		Beaded	
WATERTIGHT AQL		1.5	
ORIGIN COUNTRY		China/Malaysia	

* Specifications based on size Large glove

PHYSICAL PROPERTIES

	PRE-AGING	POST-AGING
TENSILE STRENGTH:	20 MPa	19 MPa
ELONGATION:	560%	550%

INTEGRATED TECHNOLOGIES

DRY CORE Moisture Management Technology: Absorbent lining wicks away moisture for added comfort in extended use.

ECOTEK Sustainable Technology: Product has been tested per ASTM D5526*



STANDARDS & CERTIFICATIONS

EN ISO 21420:2020
EN 455-2000-2015
ASTM D6319-19
ASTM F1671-13
ASTM F739-12
Reach EU 1907/2006
EU 2016/425

ANSI/ISEA 105-2016
CAT III Complex Design
FDA 21 CFR 177.2600



Please visit swssglobal.com/symbols for information on standards used on this document.

ORDERING

CAT NO.	MFG NO.	SIZE	PALM WIDTH	PACKAGING
17441094	N106551	XS 5½ – 6	3.0" 76mm	50 gloves per box 10 boxes per case
17441095	N106552	S 6½ – 7	3.4" 87mm	50 gloves per box 10 boxes per case
17441096	N106553	M 7½ – 8	3.8" 97mm	50 gloves per box 10 boxes per case
17441097	N106554	L 8½ – 9	4.3" 109mm	50 gloves per box 10 boxes per case
17441098	N106555	XL 9½ – 10	4.5" 114mm	50 gloves per box 10 boxes per case
17441099	N106556	2XL 10½ – 11	4.9" 125mm	50 gloves per box 10 boxes per case

* EcoTek gloves tested to ASTM D5526-12 Standard Test Method for Determining Anaerobic Biodegradation of Plastic Materials Under Accelerated Landfill Conditions. Results are 92.6% biodegradation in 60% solids landfill at 945 days. Future results cannot be predicted/extrapolated. If you need more information on the test reports, send email to cs@swssglobal.com.

APPLICATIONS

Chemical Handling
Clinical
Laboratory
Liquid Handling
Pharma Production
Tattooing and Cosmetics

Keep out of sunlight. Store in a cool, dry place.
Keep away from sources of ozone or ignition.



R_N10655X0923

Distributed by Fisher Scientific. Contact us today:

In the United States

Order online: fishersci.com

Call customer service: 1-800-766-7000

In Canada

Order online: fishersci.ca

Call customer service: 1-800-234-7437

